

APPLICATIONS

- Microtunneling
- Any type of line pulling activity: highway, railroad, and creek crossings
- Bundled pulls

COMPLIANT WITH:

(standards/regulations)

- US DOT CFR 192 and 195
- CSA Z662
- ASME PCC-2 Article 401
- ISO 24817



BENEFITS:

- Reduces pulling friction due to high lap shear strength of the methylmethacrylate adhesive
- Each Casing Spacer unit can be installed in less than thirty minutes and cured/pulled within two hours after the last unit is installed
- Any abrasion during the pipe pull occurs at the outer layer of the sleeve instead of the coating of the carrier pipe
- No environmental hazards or hot work permit required
- Resistance to sliding prevents spacer bunching and cathodic protection shorts

Casing Spacer

QUALIFICATION DATA

PROPERTIES	VALUE
Tensile Strength (ASTM D638)	2,000 - 2,250 psi (13.8 MPa - 15.5 MPa)
Modulus	35,000 - 50,000 psi (241.3 MPa - 344.7 MPa)
Strain to Failure	15 - 25%
Lap Shear Cohesive Strength (ASTM D1002)	1,250 - 1,500 psi (8.6 MPa - 10.3 MPa)
Service Temperature	180°F (82°C)

WARRANTY CSNRI routinely implements product improvements. Please contact your local distributor or office for the most current product specifications. CSNRI warrants the quality of this product when used according to directions.

PS_0122 ISO 9001 Certified

